

# HI EP Deck Top coat

## Product data sheet

### Characteristics & Specification Data

Description	HI EP Deck Top Coat is a two-pack, solvent-free
Characteristics	HI EP Deck Top Coat is a wear resistant, providing a smooth surface with high chemical resistance. HI EP Deck Top Coat cures quickly and
Area of application	HI EP Deck Top Coat is designed particularly as a high performance coating for "Heavy Duty" deck systems for ships and offshore installations. Recommended for decks, helidecks, walkways, heavy duty traffic areas, loading areas
Color	RAL 7038, RAL 6002, other colours available on
Finish	N.A.
Primers	Apply onto a solvent-free base
Topcoats	Can be overpainted with solvent-free epoxy.
Dry Film Thickness	1,0 - 1,3mm
Wet Film Thickness	1,0 - 1,3mm
Solids Content	> 99%
Theoretical Coverage Rate	1,0 - 1,7 kg/m <sup>2</sup> .
Dry Temperature Re-	Softens if more than 60°C.

### Surface Preparation

General	Surface cleaned and prepared.
Steel	Consult technical data for HI EP Sealer. The temperature of the steel substrate must be minimum 3°C above dew point.
Concrete	N.A.

### Application Equipment

Equipment	Apply HI EP Deck Top Coat (A+B) in the required thickness with rubber-squeegee or paint brush.  Antiskid: Apply antiskid to top layer of HI EP Deck Top Coat with a squeegee.  Distribute Antiskid with a paint roller.
-----------	--

### Mixing & Thinning

Mixing	Mix part A and part B thoroughly with agitator prior to use, minimum 1 minute.
Mixing ratio	Part A: Part B=3,7:1 (by weight). Part A: Part B=2,7:1 (by volume). The product is delivered in correct mixing proportions.
Thinning	<b>Do not use thinner.</b>
Pot Life	20 minutes at 20 °C.

### Cleaning & Safety

Cleaning	Tools may be cleaned by use of an aromatic solvent such as xylene, toluene, ethyl acetate.
Safety	Protective clothing for working with epoxy.
Ventilation	Good ventilation when heating of rooms.
Caution	Consult material safety data sheet.

### Application Conditions

	Coating	Surface	Ambient	Humidity
Normal	15-30°C	15-30°C	15-30°C	0-85%
Minimum	10°C	5°C	5°C	0%
Maximum	30°C	50°C	45°C	85%

Do not apply when surface temperature is less than 3°C above dew point.

#### Business address:

Hummervoll Industribellegg AS  
Sanddalsringen 3,  
5225 Nesttun - Norway

email: hummervoll@hummervoll.no

Phone: +47 55922700

www.hummervoll.no

# HI EP Deck Top coat

## Product data sheet

### Technical Data

At 20°C and 50% RH (relative humidity)

Tack free	3 h.
Fully cured	4-7 days.
Specific gravity	1,33 g/cm <sup>3</sup> .
Viscosity	800 cp at 25 °C.

### Curing Schedule

Temperature	Recoating
5°C	16 h.
10°C	10 h.
20°C	5 h.

### Packaging & Storage

Sales Unit	16 kg set.
Storage (General)	To be stored unopened and under dry conditions.
Storage Temperature & Humidity	Storage temperature should be kept between 5-40 °C.
Shelf Life	36 months at max 23°C.

### Further information

When other products are to be used together with this material, the technical data sheets must be checked. This is to make sure they are compatible with each other.

After many years experience, Hummervoll Industribelegg AS has a very good technical and practical knowledge. We are happy to assist with our expertise.

#### Business address:

Hummervoll Industribelegg AS  
Sanddalsringen 3,  
5225 Nesttun - Norway

email: [hummervoll@hummervoll.no](mailto:hummervoll@hummervoll.no)

Phone: +47 55922700

[www.hummervoll.no](http://www.hummervoll.no)